

Figure: 30 TAC §115.421(7)

Affected Operation	Pounds of Volatile Organic Compounds (VOC) per Gallon of Coating	Kilogram of VOC per Liter of Coating
Sheet Basecoat (Exterior and Interior) and Over-Varnish	2.8	0.34
Two-Piece Can Exterior (Base-Coat and Over-Varnish)	2.8	0.34
Two- and Three-Piece Can Interior Body Spray, Two-Piece Can Exterior End (Spray or Roll Coat)	4.2	0.51
Three-Piece Can Side-Seam Spray	5.5	0.66
End Sealing Compound	3.7	0.44